



DC 1500V



100m~6000m



Low Smoke Zero Halogen



Excellent Chemical & Oil resistance



-40℃ ~ +90℃



UV Resistance



IEC62930/EN50618



Specification 技术参数

应用范围 Application	太阳能板及光伏系统连线 Internal wiring for solar panel and photovoltaic system
认证 Approval	EN50618
额定电压 Rating voltage	DC1500V
测试电压 Test voltage	AC 6.5KV, 50Hz 5min
工作温度 Working temperature	-40~+90℃
最高线温 Max Conduct temperature	120℃
短路温度 Short circuit temperature	250℃ 5S
弯曲半径 Bending radius	4×D
寿命 Life Period	≥25 years

Structure 结构参数

标称截面 Cross Section (mm ²)	铜导体构造 Construction (No. / ±0.008mm)	导体外径 DIA. (mm)	绝缘厚度 Insulation Thickness (mm)	护套厚度 Jacket Thickness (mm)	线缆外径 Cable OD. (±0.2mm)
1×2.5	49/0.25	2.02	0.7	0.8	5.4
1×4	56/0.283	2.46	0.7	0.8	5.6
1×6	84/0.283	3.02	0.7	0.8	6.3
1×10	146/0.283	4.00	0.7	0.8	7.8
1×16	228/0.283	5.00	0.7	0.9	9.3

Package Data

Package REF 包装规格	Without Spool 包无线轴包装		With Spool 线轴包装	
	MPQ (m) 最小包装(4mm ²)	100m	200m	400m
One Pallet 单托盘(4mm ²)	14,400m	30,000m	18,000m	12,000m
20GP Container 20 尺柜	300,000m for 4mm ²			
	200,000m for 6mm ²			



Electrical Data 电气参数

标称截面 Cross Section (mm ²)	最大导体电阻 20℃ (Ω/km) Conductor Max. Resistance @20℃ (Ω/km)	最小绝缘电阻 20℃ (MΩ·km) Insulation Min. Resistance @20℃ (MΩ·km)	最小绝缘电阻 90℃ (MΩ·km) Insulation Min. Resistance @ 90℃ (MΩ·km)
1×2.5	7.98	690	0.690
1×4	5.09	579	0.579
1×6	3.39	499	0.499
1×10	1.95	419	0.419
1×16	1.24	393	0.393

Properties 物理性能

绝缘电阻 (20℃) Insulation resistance @20℃	≥ 709 MΩ·Km (4mm ²)
绝缘电阻 (90℃) Insulation resistance @90℃	≥ 0.709 MΩ·Km (4mm ²)
护套表面电阻 Surface resistance of sheath	≥10 ⁹ Ω
成品电缆耐电压 Voltage test of finished cable	AC 6.5KV 5min, No break
绝缘线芯直流耐压 DC Voltage test of insulation	1800V, 240h85℃ No break
绝缘抗张强度 Tensile strength of insulation	≥8.0Mpa
护套抗张强度 Tensile strength of sheath	≥8.0Mpa
护套伸长率 elongation of sheath	≥125%
护套热收缩 Shrinkage resistant	≤2%
耐酸碱 Acid and alkali resistant	EN60811-404 23 7× 24h
耐臭氧 Ozone resistant	EN 60811-403 EN 50396
耐气候性 UV resistant	EN 50289-4-17
动态穿透 Dynamic penetrate force	EN 50618-AnnexE EN 50289-4-17
低温卷绕 (-40℃,16h) Winding at low temperature	EN 60811-504
低温冲击 (-40℃, 16h) Impact at low temperature	EN 60811-506
耐燃 Fire performance	IEC60332-1-2
氯溴含量 Clad Br Content	EN 50252-1 Annex B
热寿命 Thermal endurance Test	EN60216-1,EN60216-2, TI120

* Customized options available, for more information, please contact LEADER sales team: info@leadergroup-cn.com.

